





Vivace Decorative (Glazed Porcelain)



Rice - RIC NATVIVRIC44G 4"x4" Pressed Porcelain Field Tile - Gloss



Rice - RIC NATVIVRIC49G 4"x9" Pressed Porcelain Field Tile - Gloss



Rice - RIC NATVIVRIC918M 9"x18" Pressed Porcelain Field Tile - Matte



Fossil - FOS NATVIVFOS44G 4"x4" Pressed Porcelain Field Tile - Gloss



Fossil - FOS NATVIVFOS49G 4"x9" Pressed Porcelain Field Tile - Gloss



Fossil - FOS NATVIVFOS918M 9"x18" Pressed Porcelain Field Tile - Matte



Atlantic - ATL NATVIVATL44G 4"x4" Pressed Porcelain Field Tile - Gloss



Atlantic - ATL NATVIVATL49G 4"x9" Pressed Porcelain Field Tile - Gloss



Atlantic - ATL NATVIVATL918M 9"x18" Pressed Porcelain Field Tile - Matte



Caviar - CAV NATVIVCAV44G 4"x4" Pressed Porcelain Field Tile - Gloss



Caviar - CAV NATVIVCAV49G 4"x9" Pressed Porcelain Field Tile - Gloss



Caviar - CAV NATVIVCAV918M 9"x18" Pressed Porcelain Field Tile - Matte



Motif Rice NATVIVMOTRIC44G 4"x4" Pressed Porcelain Deco - Gloss



Incline Rice NATVIVINCRIC44M 4"x4" Pressed Porcelain Deco - Matte



Roads Atlantic NATVIVROAATL99M 9"x9" Pressed Porcelain Deco - Matte



Peak Caviar NATVIVPEACAV99G 9"x9" Pressed Porcelain Deco - Gloss



Roads Caviar NATVIVROACAV99M 9"x9" Pressed Porcelain Deco - Matte

SIZING & PACKAGING

Type	Shape	Item	Code	Size	Descript	ion		Pcs / Ctn	Sf / Ctn
Field		NAT	VIV•••44G	4"x4"	Pressed F	Porcelain Field Tile - C	Gloss	40	5.38
		NAT	VIV•••49G	4"x9"	Pressed F	Porcelain Field Tile - C	Gloss	20	5.38
		NAT	VIV918M	9"x18"	Pressed F	Porcelain Field Tile - N	∕latte	10	10.87
Deco		NAT	VIVMOTRIC44G	4"x4"	Pressed F	Porcelain Deco - Glos	s (Motif Rice)	40	5.38
		NAT	VIVINCRIC44M	4"x4"	Pressed F	Porcelain Deco - Matt	e (Incline Rice)	40	5.38
		NAT	VIVPEACAV99G	9"x9"	Pressed F	Porcelain Deco - Glos	s (Peak Caviar)	20	10.80
		NAT	VIVROACAV99M	9"x9"	Pressed F	Porcelain Deco - Matt	e (Roads Caviar)	20	10.80
		NAT	VIVROAATL99M	9"x9"	Pressed F	Porcelain Deco - Matt	e (Roads Atlantic)	20	10.80
Trim		Ø NAT	VIV•••LNRG	1/2"x12"	Pencil Lir	ner - Gloss		50	_
ANSI TECHN	NICAL SPECIFICATIO	DNS - Gloss						Shade Vari	ation
ANSI TECHN	NICAL SPECIFICATIO		Frost	Caratah	Prophing	Water	Chamical	Shade Vari	ation
ANSI TECHN	DCOF Acutest	PEI Rating ASTM# C1027	Frost Resistant ASTM# C1026	Scratch Resistance MOHS	Breaking Strength ASTM# C648	Water Absorption ASTM# C373	Chemical Resistance ASTM# C650	V1 V2	V4
ANSI TECHN	DCOF	PEI Rating	Resistant	Resistance	Strength	Absorption	Resistance		V4
Results	DCOF Acutest	PEI Rating ASTM# C1027	Resistant ASTM# C1026	Resistance MOHS	Strength ASTM# C648	Absorption ASTM# C373	Resistance ASTM# C650	V1 V2	V4
Results	DCOF Acutest N/A	PEI Rating ASTM# C1027	Resistant ASTM# C1026	Resistance MOHS 6 Scratch Resistance	Strength ASTM# C648	Absorption ASTM# C373	Resistance ASTM# C650	V1 V2	v4
Results	DCOF Acutest N/A NICAL SPECIFICATIO	PEI Rating ASTM# C1027 3 ONS - Matte	Resistant ASTM# C1026 Unaffected Frost Resistant	Resistance MOHS 6 Scratch Resistance	Strength ASTM# C648 ISO ≥ 600 N Breaking Strength	Absorption ASTM# C373 ≤ 0.5% Water Absorption	Resistance ASTM# C650 Unaffected Chemical Resistance	V1 V2 V3-Model	v4
Results ANSI TECHN	DCOF Acutest N/A NICAL SPECIFICATIO DCOF Acutest ≥ 0.42	PEI Rating ASTM# C1027 3 DNS - Matte PEI Rating ASTM# C1027	Resistant ASTM# C1026 Unaffected Frost Resistant ASTM# C1026	Resistance MOHS 6 Scratch Resistance MOHS	Strength ASTM# C648 ISO ≥ 600 N Breaking Strength ASTM# C648	Absorption ASTM# C373 ≤ 0.5% Water Absorption ASTM# C373	Resistance ASTM# C650 Unaffected Chemical Resistance ASTM# C650	V1 V2 V3-Model	v4
Results ANSI TECHN Results	DCOF Acutest N/A NICAL SPECIFICATIO DCOF Acutest ≥ 0.42	PEI Rating ASTM# C1027 3 DNS - Matte PEI Rating ASTM# C1027	Resistant ASTM# C1026 Unaffected Frost Resistant ASTM# C1026	Resistance MOHS 6 Scratch Resistance MOHS	Strength ASTM# C648 ISO ≥ 600 N Breaking Strength ASTM# C648	Absorption ASTM# C373 ≤ 0.5% Water Absorption ASTM# C373	Resistance ASTM# C650 Unaffected Chemical Resistance ASTM# C650	V1 V2 V3-Model	v4
Results ANSI TECHN Results	DCOF Acutest N/A NICAL SPECIFICATIO DCOF Acutest ≥ 0.42	PEI Rating ASTM# C1027 3 ONS - Matte PEI Rating ASTM# C1027	Resistant ASTM# C1026 Unaffected Frost Resistant ASTM# C1026 Unaffected	Resistance MOHS 6 Scratch Resistance MOHS 7	Strength ASTM# C648 ISO ≥ 600 N Breaking Strength ASTM# C648 ISO ≥ 600 N	Absorption ASTM# C373 ≤ 0.5% Water Absorption ASTM# C373	Resistance ASTM# C650 Unaffected Chemical Resistance ASTM# C650 Unaffected	V1 V2 V3-Model	v4

APPLICATIONS - Matte

Residential • † • • • • • • • • Commercial • † • • • • • • • • • • • • • • • • •		Floors	Walls	Countertops	Shower Floors	Shower Walls	Pools/Spas
Commercial • † • • • • •	Residential	• †	•	•	•	•†	•
	Commercial	• †	•	•	•	•†	•



LEGEND

Product rated for Interior & Exterior use

∅ Applications & ANSI Technical Specifications do not apply

• Product rated for Interior use only

* Special Order only

† May be suitable for Exterior Floors



[†] The TCNA does not rate products for exterior floors. Project specifier must determine product suitability for exterior floor applications by evaluating specific project conditions, type of use, traffic, drainage, expected contaminants (such as water, oil, grease, etc.), wear, maintenance, and manufacturer's specifications and guidelines. Use caution--product may not be suitable for pool decks. Not suitable for ramps. No polished tiles; only textured surfaces may be suitable.

The maximum allowable installation offset is 33%. Minimum grout joint must be 3/16 inch. Please refer to the most current TCNA Handbook. Use of a leveling system is strongly recommended.

For installation of all gloss, polished, polished glazed, lappato, and honed porcelain/ceramic tiles, use a grout release prior to grouting to prevent absorption of the grout into the tile's micropores. Use a grout color that matches the predominant color of the tile. Refer to grout manufacturer's specifications to ensure use of proper grout. Refer to tile manufacturer's specifications to determine if the polished or honed tile is appropriate for commercial applications. Tiles with a polished finish are not appropriate for wet or exterior floor applications. Do not use acidic cleaners.

Merchandising materials and samples are for general reference only and representative of a product's potential characteristics. Tile is subject to variation in color/shade, size, texture, and finish. Field, mosaic and trin tile may not match exactly. Blend tiles from different boxes to achieve consistent shade distribution. Installer and end user must conduct a dry mock layout under proper lighting conditions to inspect the product. Installation constitutes product acceptance. Improper installation, application, use, care and maintenance voids warranty. Reference the TCNA Handbook and ANSI for installation guidance.

We reserve the right to make product changes at any time without notice.